

// 076AE

**Oxygen welding 20 bar (300 psi)
EN ISO 3821****Tube:** black SBR.**Reinforcement:** high tensile textile cords.**Cover:** blue SBR/EPDM - abrasion and ozone resistant.**Application:** oxygen welding.**Constant operation:** -25 °C +80 °C (-13 °F +176 °F)

												
mm	in	mm	in	bar	psi	bar	psi	mm	in	%	kg/m	lb/ft
6,0	1/4"	13,00	0,51	20	300	60	900	80,0	3,15		0,170	0,12
8,0	5/16"	15,00	0,59	20	300	60	900	80,0	3,15		0,200	0,14
10,0	3/8"	17,00	0,67	20	300	60	900	100,0	3,94		0,240	0,17

// 076AH

**Acetylene welding 20 bar (300 psi)
EN ISO 3821****Tube:** black SBR.**Reinforcement:** high tensile textile cords.**Cover:** red SBR/EPDM - abrasion and ozone resistant.**Application:** acetylene welding.**Constant operation:** -25 °C +80 °C (-13 °F +176 °F)

												
mm	in	mm	in	bar	psi	bar	psi	mm	in	%	kg/m	lb/ft
6,0	1/4"	13,00	0,51	20	300	60	900	80,0	3,15		0,170	0,12
8,0	5/16"	15,00	0,59	20	300	60	900	80,0	3,15		0,200	0,14
10,0	3/8"	17,00	0,67	20	300	60	900	100,0	3,94		0,240	0,17

// 076AI

**LPG welding 20 bar (300 psi)
EN ISO 3821****Tube:** black NBR.**Reinforcement:** high tensile textile cords.**Cover:** orange SBR/EPDM - abrasion and ozone resistant.**Application:** LPG welding.**Constant operation:** -30 °C +80 °C (-22 °F +176 °F)

												
mm	in	mm	in	bar	psi	bar	psi	mm	in	%	kg/m	lb/ft
6,0	1/4"	13,00	0,51	20	300	60	900	80,0	3,15		0,160	0,11
8,0	5/16"	15,00	0,59	20	300	60	900	80,0	3,15		0,190	0,13
10,0	3/8"	17,00	0,67	20	300	60	900	100,0	3,94		0,220	0,15